Röchling Industrial

Röchling Industrial SE & Co. KG • Postfach 12 49 • D-49724 Haren/Germany

Access Plastics LTD
Unit 16, Ashbourne Ind. Estate
County Meath

Jan Edel
Chemist
Chemical Processing Industry

Tel.: +49 5934 701-287
JEdel@roechling.com

Chemical Resistance Statement

02. Jul. 2026

Dear Mr. David McGowan,

we confirm chemical resistance of PVC-U (**Trovidur® EC**) as follows:

	Temperature [°C]		
Name	**20**	**40**	**60**
Hydrochloric Acid 35%	+	+	+
Sulfuric Acid 60%	+	+	+
Nitric Acid 53%	+	+	o
Formic Acid 60%	+	o	-
Lactic Acid	+	+	+
Caustic Soda	+	+	o
Ammonia Water	+	+	+
Sodium metabisulfite	+	+	+
Acetone	-	-	-
Ethyl Alcohol	+		
Butyl Alcohol	+		
Formaldehyde 40%	+		
Benzene	-	-	
Carbon disulphide	-	-	
Solution of Spraying Paint	-	-	-
Chlorine Gas	-	-	-
Ammonia/Other Waste Gases	+		
Natural Gas	+		
Coal Gas	+		
Bleaching Solution	+	+	
Sea Water / Salt Water	+	+	+
Fermented Alcohol	+		
Starch (Carbohydrate) Solution	+	+	+

This information is based on generally available information, our own tests and experience, as well as information from the raw material suppliers. Please note that no tests were performed with the specific product Trovidur® EC Clad.

If you have any questions, please do not hesitate to contact us.

Kind regards

Röchling Industrial SE & Co. KG

i. A. Jan Edel

*In view of the many factors that may affect fabricating and application, these data do not relieve fabricators from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or suitability for a specific purpose.